

Highlights

 Available in a variety of surface textures such as grooved, embossed, plain, and perforated Polyurethane impregnated felt pad, non-woven

SUBA™ 600

SUBATM polishing pads are polyurethane-impregnated polyester felts. They are specifically designed for stock and intermediate polishing where achieving a high-precision surface is critical. SUBATMa pads should be used in combination with each other and with final polishing pads to produce a haze-free, low-defect finish in dual or multi-step processes. SUBATM pads are ideal for a wide variety of materials including semiconductor wafers, glass, ceramics, special metals, and plastic.

Typical applications

Sapphire, silicon carbide, gallium nitride, silicon nitride, silicon, etc.

Polishing pad	Base material	Compressibility [%]	Hardness	Hardness test	Thickness [mils]
SUBA™ 600	Felt	4.00	80	Asker C	50
SUBA™ 800	Felt	4.00	82	Asker C	50
SUBA™ X	Felt	13.25	47	Shore D	50
SUBA™ IV	Felt	13.50	44	Shore D	50
SUBA™ IV.150	Felt	13.50	44	Shore D	150
GS polishing pad	Felt	5.00	45	Shore D	150

The data presented is a statistical representation for comparison purposes. The values are not necessarily representative of the COA specifications.

All information is non-binding and provided for information purposes only. Subject to change without notice. - SUBA_600_datasheet_de-en_2024-04-08 - 04.01

PUREON



The high polymer concentration within the SUBA™ 600 produces a hard, low-compressible pad that is durable under high-pressure applications.



Pureon offers a variety of slurries in a wide range of viscosities and custom formulations to match SUBA™ pads. We are happy to assist you in finding the best suitable products.



Pureon offers a wide range of customized solutions. Get in touch with us

Product specifications

Base material Felt
Shelf life 12 months

Application recommendations

Handling

Apply only to a clean, dry surface at room temperature. If an appropriate solvent, such as isopropyl alcohol, is used to clean the platen after a pad removal, allow the platen to dry completely and return to room temperature before applying a new pad. Solvents remaining on the platen or an unusually cold platen will lower PSA adhesion.

When applying the pad to the platen, peel the release liner from one edge of the pad. Fold liner back approximately two inches. Align the pad with the edge of the platen and adhere. In one continuous movement, slowly peel the remaining release liner off the pad while pressing the pad down on the platen. The application should be smooth and uniform with even pressure from the pad mounting tool (such as a flat disk or hand roller).

Do not try to reposition pads with PSA adhesive.

Storage

Product should be stored and transported in the original packaging. The product should be stored in temperatures between 10 °C to 24 °C (50 °F to 75 °F) and < 50 % humidity. Exposure for six (6) months or less to conditions between -17 °C to 48 °C (0 °F and 120 °F) and/or at relative humidity of up to 100 % will not impact the product performance as long as the release liner remains intact and attached to the PSA. If the product is exposed to temperatures and humidity outside the recommended conditions, it may still be acceptable for use. In all cases, the product should be allowed to return to normal room temperatures prior to use.

Disposal

... Dispose of in accordance with all applicable local regulations.

 $\mathsf{SUBA^{TM}} \text{ is a registered trademark of DuPont. Pureon is an authorized distributor for DuPont.}$

