



Highlights

- Small particle size and tight distribution result in excellent surface quality, removal rate, and repeatability
- Suspension package facilitates uniform delivery of abrasive to polishing workpiece and prevents settling in the tools and lines
- Designed to be easy to clean off parts and tools, resulting in less rework and higher yields
- Compatible with polishing pads, pitch, CNC tools, and spindle polishers

Cerium oxide suspensions

ULTRA-SOL®

ULTRA-SOL® cerium oxide slurries are designed for the precision polishing of borosilicate glass, fused silica, glass ceramics, and other optical materials. They feature a small, tightly distributed cerium oxide particle in a unique suspension that minimizes settling and facilitates cleaning. In addition, these slurries are highly concentrated to provide maximum flexibility through on-site dilution. They have quickly proven themselves to be a superior cerium oxide polish to many existing products on the market.

ULTRA-SOL® cerium oxide slurries process performance exceeds industry specifications for sleek, scratch / dig, surface finish, and elimination of sub-surface damage on precision glass workpieces. Their unique chemistry allows for uniform and permanent suspension of the abrasive, which provides consistent and repeatable superior surface finishes, and ease of use in production environments.

Applications

Fused silica, glass, zerodur

Order code	Base material	Particle size [µm]	pH	Solids content [%]
ULTRA-SOL® 1001	Cerium oxide	1,15	9,7	15,0
ULTRA-SOL® 1000HP	Cerium oxide	0,95	8,5	10,0
ULTRA-SOL® OPTIQ	Cerium oxide	0,45	8,2	45,0



ULTRA-SOL® cerium oxide slurries achieve surface finishes under 5 Å on many different optical materials.



Pureon ready-to-use slurries are available in customer-tailored formulations in a wide range of viscosities.



Pureon offers a wide range of customized solutions. Get in touch with us.

Product specifications

Base material Cerium oxide
Shelf life 12 months

Order information

Packing 1 gal jugs.
Other sizes available upon request.

Unit of measure Gallon [gal]

Instructions

Safety To avoid skin or eye irritation, use appropriate personal protective equipment according to MSDS. Follow all MSDS Safety datasheets, label precautions, and industrial safety and hygiene practices when handling or using this product.

Homogenization For consistent performance, ensure that the suspension is completely homogenized prior to use. Suspensions can separate if stored over extended periods of time and if exposed to variable temperatures.

Dilution This slurry is designed as a ready-to-use product directly from the container. If the slurry is to be used in a diluted form, use only high-quality deionized water (> 18 M ohm) for the dilution. The product should be mixed periodically (10 to 20 minutes per day) by recirculation or mechanical stirring to ensure that the particles are uniformly suspended. To avoid possible scratching issues, storage and re-use of on-site diluted slurry is not recommended without proper mixing and filtration.

Due to the unique formulation of this slurry, pH adjustment is not recommended. For a different pH, please contact your Pureon representative.

Storage Recommended ... 4 °C – 33 °C / 40 °F and 90 °F
Sort term 0 °C – 38 °C / 32 °F and 100 °F

Products should be allowed to return to room temperature prior to use. Storage outside the recommended conditions may result in irreversible product damage.

Disposal Dispose of in accordance with all applicable local regulations.

Contact

sales@pureon.com
www.pureon.com

